

In the Abstract

{Document Name}—Abstract

{Abstract}

{Problem to be Solved}

~~To provide a biaxially oriented white film for thermal transfer recording which has low specific gravity required as a thermal transfer film, high whiteness and cushion factor, and is excellent in crease resistance, and has a high level compatibility between high sensitivity and productivity when used as a substrate of a receiving sheet, and a receiving sheet for thermal transfer recording using the same.~~

{Means for Solving the Problem}

(1)—~~A biaxially oriented white polypropylene film for thermal transfer recording characterized in that it is~~including ~~a film comprising of~~containing ~~polypropylene resin of which~~having a β -crystal ratio isof about 30% or more and a melting temperature isof about 140 to about 172°C, and which has a substantially non-nucleus voids, a void ratio of about 30 to about 80% and a sum of strengths of longitudinal direction and of transverse direction of the film at 2% elongation (F2 value) being in the range of about 10 to about 70 MPa and a surface glossiness being in the range of about 10 to about 145 % ~~(the first configuration).~~

(2)—~~A biaxially oriented white polypropylene film for thermal transfer recording characterized in that a skin layer (B layer) of which surface glossiness is 10 to 145 % is laminated to at least one side of a core layer (A layer) of polypropylene resin of which β -crystal ratio is 30% or more, melting temperature is 140 to 172°C, which has a substantially non-nucleus voids, a void ratio of 30 to 80%, and a sum of the strengths of longitudinal direction and of transverse direction of the film at 2% elongation (F2 value) being in the range of 10 to 70 MPa (the second configuration).~~

(3) — A biaxially oriented white polypropylene film for thermal transfer recording in which a skin layer (B layer) of which surface glossiness is in the range of 10—145 % is laminated to at least one side of a core layer (A layer) characterized in that a sum of strengths of longitudinal direction and of transverse direction of the film at 2% elongation (F2 value) is in the range of 30 to 100 MPa and that the film has β -crystal activity (the third configuration).

(4) — A biaxially oriented white polypropylene film for thermal transfer recording which is a film in which a skin layer (B layer) having a half-crystallization time of 60 seconds or less and a surface glossiness of 30 to 145 % is laminated at least on one side of a core layer (A layer) which consists of polypropylene resin having a substantially non-nucleus void, characterized in that it is a film of a specific gravity of 0.3 to 0.7 and has β -crystal activity (the fourth configuration).